

PEMC[™]

Polyamine Epoxy Mid-Coat



Building
&
Transportation



Oil, Gas
&
Industrial



Offshore
&
Onshore



Water
&
Wastewater



PRODUCT DESCRIPTION

CTech-LLC[®] Polyamine Epoxy Mid-Coat (**PEMC[™]**) is an excellent choice for use as a floor mid-coat of a high-performance epoxy based coating system. The PEMC[™] is based on epoxy resin and special color pigments, antioxidants and alkalis to form a two-component mid-coat for use in commercial, industrial and residential floor applications.

Product made mainly of epoxy resin and modified amine resin which is suitable for properly prepared carbon steel, stainless steel, aluminum, concrete, galvanized steel, shop primed steel and thermally sprayed zinc substrates. With proper top coating, the PEMC[™] demonstrates excellent resistance to moisture and chemicals, including solvents, acids, and alkalis.

ADVANTAGES

- A high performance two pack epoxy mid-coat with excellent adhesion
- Anti-chemical and corrosion
- Easy surface cleaning
- No cracking and water-proof product
- Low odour, environmental friendly.

TECHNICAL DATA

Finish	All color spectra
Recommended D.F.T.	1500 microns
Mixed Ratio (Base : Curing Agent)	100 : 18
Volume Solids Ratio	100%
Mass Volume Density	1.5 gr/cm ²
Induction time	30 minutes
Curing Time	6-8 Hours
Full Cure After	7 Days
Pot Life	25-35 minutes

* Testing temperature: 21°C

TYPICAL USES

As a high quality floor mid-coating for a wide range of substrates. The PEMC[™] is designed for use in commercial, industrial and residential floor applications

INSTALLATION PROCEDURE

SURFACE PREPRATION

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, mill scale, form release agents, curing compounds, loose and flaking paint and other surface contaminants.

MIXING

- First stir base component and hardener separately.
- Using a mixer at low speed, blend correct proportions of base and hardener for three to five minutes until completely blended.
- Care must be taken to assure both components are completely mixed in order to avoid partially cured spots in the coating.
- Allow to induct for 30 minutes.

APPLICATION

Pour the mixture on the floor and spread using medium pile hair roller or rubber spreader or by spray machines.

STORAGE & SHELF LIFE

The material should be stored at temperatures between 5°C to 35°C to ensure shelf life.

Shelf life is 18 months when stored as recommended in original unopened containers

CAUTION

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet

(SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations.

CTech-LLC[®]

CYTEC's Composite Technology
technical@ctech-llc.com
info@ctech-llc.com
www.CTech-LLC.com

IMPORTANT NOTE:

Before using any CTech-LLC[®] product, the user must review the most recent version of the product's technical data sheet, material safety data sheet and other applicable documents, available at www.ctech-llc.com.

WARANTY:

CTech-LLC[®] warrants its products to be free from manufacturing defects. Buyer determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to replacement of product. Any claim for breach of this warranty must be brought within one month of the date of purchase. CTech-LLC[®] shall not be liable for any consequential or special damages of any kind, resulting from any claim or breach of warranty, breach of contract, negligence or any legal theory. The Buyer, by accepting the products described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before utilizing.
